

PROCEDURE

DEVCON REPAIR

WHAT IS INCLUDED IN THE KIT



50 ml Devcon Cement



Mixing Nozzle

NEEDS TO BE SOURCED SEPARATELY (NOT INCLUDED WITH KIT)

Use ELLSWORTH
DISPENSING GUN
EA51-1 TO 1/2 TO 1
OR EQUIVALENT



Drop Cloth



Safety Glasses



Safety Gloves

INSTALLATION INSTRUCTIONS



**Devcon is highly flammable. Only use in well-ventilated areas.
Always wear protective gloves and safety glasses when handling.**

Devcon and Ellsworth dispensing gun assembly visual guide



NOTE: Ellsworth dispensing gun model EA51-1 or equivalent will need to be sourced separately.

1. Use a drop cloth to cover any area of the spa or surroundings that will be exposed during the Devcon repair. The Devcon may cause permanent damage to surfaces it contacts. Be sure to mask off any plumbing lines and compression fittings before starting the repair.
2. Normal working time for the Devcon supplied in the Crack Repair Kits is between ten (10) and twenty (20) minutes at seventy (70) degrees Fahrenheit.
3. Assemble the Devcon applicator and place assembly into Ellsworth dispensing gun EA51-1 to 1/2-1 or equivalent (see visual guide above).
4. The Devcon should be allowed to set up for a minimum of 45 minutes.